

# Agilus30



## PolyJet Rubberlike Material

Agilus30™ is a superior rubber-like PolyJet™ photopolymer family ideal for advanced design verification and colorful rapid prototyping. Get more durable, tear-resistant prototypes that can stand up to repeated flexing and bending and design validation. With a Shore A value of 30 in all Agilus30 versions you can accurately simulate the precise colorful look, feel and function of rubber-like products. 3D print rubber surrounds, overmolds, soft-touch colorful coatings, living hinges, jigs and fixtures, wearables, consumer goods, grips and seals with surface texture.

Mechanical Properties	Test Method	Value		
		Black / Translucent	White	Cyan/Magenta/Yellow
Tensile Strength	ASTM D-412	2.4 – 3.1 MPa (348 – 450 psi)	2.1-2.6 MPa (305 – 377 psi)	2.2 – 2.6MPa (319-377 psi)
Elongation at Break	ASTM D-412	220 – 270%	185 – 230%	315 - 335%
Compressive Set	ASTM D-395	6 – 7%	6 – 7%	6 – 7%
Tensile Tear Resistance	ASTM D-624	4 – 7 Kg/cm (22 – 39 lb/in)	4 – 7 Kg/cm (22 – 39 lb/in)	4.1-4.4 kg/cm (23-25 lb/in)

  

Other	Test Method	Value		
		Black / Translucent	White	Cyan/Magenta/Yellow
Shore Hardness	ASTM D-2240	30 – 35 Scale A	30 – 40 Scale A	28-33 Scale A
Polymerized Density	ASTM D-792	1.14 – 1.15 g/cm <sup>3</sup>	1.14 – 1.15 g/cm <sup>3</sup>	1.14 – 1.15 g/cm <sup>3</sup>

  

System Availability	Layer Thickness Capability	Support Structure	Available Color
<a href="#">Objet260/350/500</a> <a href="#">Connex1/2/3™</a>	High Speed mode: 30 microns (0.0012 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input type="checkbox"/> Translucent <input checked="" type="checkbox"/> Black
<a href="#">Stratasys J735™/</a> <a href="#">Stratasys J750™</a>	High Mix mode: 27 microns (0.001 in.) High Speed mode: 27 microns (0.0011 in.)*	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White <input checked="" type="checkbox"/> Cyan <input checked="" type="checkbox"/> Magenta <input checked="" type="checkbox"/> Yellow
J4100™	High Speed mode: 27 microns (0.001 in.)	SUP705 (WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent
J826™ Prime / J835™ Prime / J850™ Prime / J850 Pro	High Mix mode: 27 microns (0.001 in.) High Speed mode: 27 microns (0.0011 in.)*	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White <input checked="" type="checkbox"/> Cyan <input checked="" type="checkbox"/> Magenta <input checked="" type="checkbox"/> Yellow

\*Not available for Agilus30™ Colors (Cyan, Magenta, Yellow)

## Stratasys Headquarters

7665 Commerce Way,  
Eden Prairie, MN 55344  
+1 800 801 6491 (US Toll Free)  
+1 952 937-3000 (Intl)  
+1 952 937-0070 (Fax)

1 Holtzman St., Science Park,  
PO Box 2496  
Rehovot 76124, Israel  
+972 74 745 4000  
+972 74 745 5000 (Fax)

[stratasys.com](http://stratasys.com)  
ISO 9001:2015 Certified

